



STAINLESS STEEL #16-54

A special formulation containing 316L stainless steel pigment to provide maximum corrosion resistance and protection against weather, sunlight, oil, and water. Dries to a satin finish. Recommended as a topcoat, not a primer. Use of a primer is always beneficial to enhance adhesion and overall durability. Dries quickly, is non-yellowing, and heat resistant up to 250°F.

Suggested Uses:

- Protect metal
- Touch up appliances
- Paint metal structures
- Touch up welds

Packaging:

UPC Code	043281000062
Cans per case	6
Shipping weight per case	7 lbs.
Container	16 fluid ounce can
Label weight	13 ounces (369 grams)
Shipping Classification	limited quantity, UN 1950
Hazard Class	2.1

Properties:

Coverage	Up to 15 square feet
Cleanup	Paint or lacquer thinner
Flammability	Extremely Flammable
Flash point	-4F
Specific Gravity	0.79
Solids Content	17%
MIR value	1.16, cannot exceed 1.25
HAPs content	33%
Storage Temperature	40-100F
Application Temperature	50-90F
Gasoline Resistance	No
Heat Resistance	250F
Resin System	Acrylic lacquer
Shelf life	Guaranteed for 2 years

Dry Time*:

To touch	5 minutes
To topcoat	10 minutes

*At 72F, 50% humidity,
 1.5 mil thickness

**Curing/Recoat time is extended with
 multiple coats and excessively thick coats**

Gloss*: Low Luster
 *as measured on a 60 degree gloss meter

Additional Information:

Not for use on internal engine parts.

Related Products:

Alumi Blast #CA16-55



or Cast Blast #CA16-48



12-8-2021